

Corrected Listing of the Claims

1. (Currently Amended) A vulcanized, automotive, fluid-conveying tubular structure exhibiting heat tolerant, pressure resistant, hydrocarbon fluid impermeable characteristics, said tubular structure consisting **essentially** of:

about 30 to 75% by weight of an ethylene-vinyl acetate copolymer ~~matrix~~, wherein said ethylene-vinyl acetate copolymer ~~matrix~~ has a vinyl acetate content greater than about 40%;

up to about 50% by weight of a polymeric material selected from the group consisting of ethylene-propylene-diene terpolymer (EPDM), styrene-butadiene rubber (SBR), acrylonitrile-butadiene rubber (NBR), ethylene-propylene rubber (EPR), butyl rubber, cis-polybutadiene, cis-polyisoprene, polyurethane, and mixtures thereof; and

about 25 to 70% by weight of one or more additives selected from the group consisting of process aids, fillers, plasticizers, metal oxides, metal hydroxides, peroxides, coagents, antioxidants and combinations thereof.

2. (Currently Amended) The tubular structure of claim 1, wherein said vinyl acetate copolymer ~~matrix~~ has a vinyl acetate content of about 60 to 90%.

3-7 Canceled

8. (Currently Amended) The tubular structure of claim 1 wherein said tubular structure consists **essentially** of:

about 45 to 60% by weight of said ethylene-vinyl acetate copolymer ~~matrix~~;

up to about 10% by weight of said polymeric material; and

about 40 to 55% by weight of said one or more additives, said one or more additives consisting **essentially** of:

(a) up to about 8% by weight of said one or more process aids selected from the group consisting of stearic acid, stearates, polyethylene, amines, oils, organic esters, organic phosphate esters and combinations thereof;

(b) about 20 to 60% by weight of one or more fillers selected from the group consisting of carbon black, silicon dioxide, fumed silica, precipitated silica, diatomaceous earth, magnesium carbonate, magnesium silicate, aluminum silicate, titanium dioxide, talc, mica, aluminum sulfate, calcium sulfate, graphite, wallastonite, molybdenum disulfide, clay, calcium carbonate and combinations thereof;

(c) up to about 15% by weight of one or more plasticizers selected from the group consisting of hydrocarbons, glycols, aldehydes, ethers, esters, ether-esters and combinations thereof;

(d) up to about 10% by weight of one or more metal oxides and/or hydroxides selected from the group consisting of zinc oxide, zinc hydroxide, magnesium oxide, magnesium hydroxide, calcium oxide, calcium hydroxide, aluminum hydroxide and combinations thereof;

(e) about 0.5 to 2.5% by weight of one or more peroxides selected from the group consisting of 2,5-dimethyl-2,5-di(t-butylperoxy)hexyne-3; 2,5-dimethyl-2,5-di(t-butylperoxy)hexane; α,α' -bis-(t-butylperoxy)-p-diisopropylbenzene; dicumyl peroxide; di-t-butyl peroxide; 1,1-bis(t-butylperoxy)-3,3,3-trimethylcyclohexane; 2,4-dichlorobenzoyl peroxide; benzoyl peroxide; p-chlorobenzoyl peroxide; 4,4-bis(t-butylperoxy) valerate; and combinations thereof.

(f) up to about 5% by weight of one or more coagents selected from the group consisting of maleimides, triallyl cyanurate, triallyl isocyanurate, diallyl terephthalate, 1,2-vinyl polybutadiene, di- and tri-functional methacrylates, diacrylates, metal ion versions thereof and combinations thereof; and

(g) up to about 3% by weight of one or more antioxidants selected from the group consisting of phenols, hydrocinnamates, hydroquinones, hydroquinolines, diphenylamines, mercaptobenzimidazoles, and combinations thereof.

9. (Canceled)

10. (Currently Amended) A vulcanized, automotive fluid-conveying hose for conveying fluids in an automotive engine cooler, transmission oil cooler, power transmission cooler, radiator or heater, said vulcanized automotive fluid-conveying hose consisting essentially of an inner tubular member, a reinforcement member on said inner tubular member, and a cover on said reinforcement member, wherein said inner tubular member consists essentially of:

about 30 to 75% by weight of an ethylene-vinyl acetate copolymer matrix, wherein said ethylene-vinyl acetate copolymer matrix has a vinyl acetate content greater than about 40%;

up to about 50% by weight of a polymeric material selected from the group consisting of ethylene-propylene-diene terpolymer (EPDM), styrene-butadiene rubber (SBR), acrylonitrile-butadiene rubber (NBR), ethylene-propylene rubber (EPR), butyl rubber, cis-polybutadiene, cis-polyisoprene, polyurethane, and mixtures thereof; and

about 25 to 70% by weight of one or more additives selected from the group consisting of process aids, fillers, plasticizers, metal oxides, metal hydroxides, peroxides, coagulants, antioxidants and combinations thereof.

11-20 (Canceled)

21. (Previously Presented) The hose of claim 10 wherein said hose is a radiator hose.

22. (Previously Presented) The hose of claim 10 wherein said hose is a heater hose.

23. (Currently Amended) The hose of claim 10, wherein said vinyl acetate copolymer matrix has a vinyl acetate content of about 60 to 90%

24. (Currently Amended) The hose of claim 10, wherein said hose consists ~~essentially~~ of:

about 45 to 60% by weight of an ethylene-vinyl acetate copolymer matrix;

up to about 10% by weight of a polymeric material selected from the group consisting of ethylene-propylene-diene terpolymer (EPDM), styrene-butadiene rubber (SBR), acrylonitrile-butadiene rubber (NBR), ethylene-propylene rubber (EPR), butyl rubber, cis-polybutadiene, cis-polyisoprene, polyurethane, polyamide, and mixtures thereof; and

up to about 40 to 55% by weight of said one or more additives, said one or more additives consisting ~~essentially~~ of:

(a) up to about 8% by weight process aid selected from the group consisting of stearic acid, stearates, polyethylene, amines, oils, organic esters, organic phosphate esters and combinations thereof;

(b) about 20 to 60% by weight filler selected from the group consisting of carbon black, silicon dioxide, fumed silica, precipitated silica, diatomaceous earth, magnesium carbonate, magnesium silicate, aluminum silicate, titanium dioxide, talc, mica, aluminum sulfate, calcium sulfate, graphite, wallastonite, molybdenum disulfide, clay, calcium carbonate and combinations thereof;

(c) up to about 15% by weight plasticizer selected from the group consisting of hydrocarbons, glycols, aldehydes, ethers, esters, ether-esters and combinations thereof;

(d) up to about 10% by weight metal oxides and/or hydroxides selected from the group consisting of zinc oxide, zinc hydroxide, magnesium oxide, magnesium hydroxide, calcium oxide, calcium hydroxide, aluminum hydroxide and combinations thereof;

(e) about 0.5 to 5% by weight peroxide selected from the group consisting of 2,5-dimethyl-2,5-di(t-butylperoxy)hexyne-3; 2,5-dimethyl-2,5-di(t-butylperoxy)hexane; α,α' -bis-(t-butylperoxy)-p-diisopropylbenzene; dicumyl peroxide; di-t-butyl peroxide; 1,1-bis(t-butylperoxy)-3,3,3-trimethylcyclohexane; 2,4-dichlorobenzoyl peroxide; benzoyl peroxide; p-chlorobenzoyl peroxide; 4,4-bis(t-butylperoxy) valerate; and combinations thereof.

(f) up to about 5% by weight coagent selected from the group consisting of maleimides, triallyl cyanurate, triallyl isocyanurate, diallyl terephthalate, 1,2-vinyl polybutadiene, di- and tri-functional methacrylates, diacrylates, metal ion versions thereof and combinations thereof; and

(g) up to about 3% weight antioxidant selected from the group consisting of phenols, hydrocinnamates, hydroquinones, hydroquinolines, diphenylamines, mercaptobenzimidazoles, and combinations thereof.

25. (Currently Presented) The tubular structure of claim 1 wherein tubular structure is a blend of said ethylene-vinyl acetate copolymer ~~matrix~~, said polymeric material and said additives.

26. (Canceled)

27. (Currently Amended) The hose of claim 10 wherein said inner tubular structure is a blend of said ethylene-vinyl acetate copolymer ~~matrix~~, said polymeric material and said additives.

28. (New) The hose of claim 10 wherein said reinforcement member is cotton fiber, polyester fiber, rayon fiber, aramid fiber or metal wire.